

**VANIMATE***To achieve more with you***VANIMATE INDUSTRIES CO., LTD**

Room 515, 3# Building, Lane 2350, Duzhuang Road, 201108, Minhang, Shanghai, China

Tel: +86-21-64908312

E-mail: info@vanimate.com

Product		C.I.No.	Type	Contents % (Fe2O3/Fe3O4)	Specific Gravity/ (g/cm3)	Bulk Density/ (g/cm3)	pH Value	Volatiles (105℃)	Water Soluble Salts (%)	Residue on 45μm Mesh (%)	Oil Absorption (%)	Tinting Strength (%)	Color Difference (Compared with Standard)	Applications
Iron Oxide Red		C.I. Pigment Red 101	VN110S	≥95	5	0.7~1.0	3~8	≤1	≤0.5	≤0.005	15~25	97~103	≤0.8	Coatings, construction, plastics
		C.I. Pigment Red 101	VN110/120 /130/190	≥95	5	0.7~1.0	3~8	≤1	≤0.5	≤0.1	15~25	95~105	≤1.0	Coatings
Iron Oxide Yellow		C.I. Pigment Yellow 42	VN313/920	≥86	4	0.4~0.6	3~7	≤1	≤0.5	≤0.1	25~35	95~105	≤1.0	Coatings
		C.I. Pigment Yellow 42	VN920S	≥86	4	0.4~0.6	3~7	≤1	≤0.5	≤0.005	25~35	97~103	≤0.8	Coatings, construction, plastics
Iron Oxide Brown		C.I. Pigment Brown 6	VN610	≥88	4.7	0.5~0.8	4~7	≤1	≤0.5	≤0.3	25~35	95~105	≤1.0	constructions
Iron Oxide Black		C.I. Pigment Black 11	VN723	≥95	4.5	0.8~1.2	5~8	≤1	≤0.5	≤0.3	15~25	95~105	≤1.0	constructions
		C.I. Pigment Black 11	VN330S	≥95	4.5	0.8~1.2	5~8	≤1	≤0.5	≤0.05	15~25	97~103	≤0.8	Coatings, construction, plastics